

SUPPLEMENTAL SPECIFICATION

**REVISIONS TO STANDARD SPECIFICATION 618 –
THERMOPLASTIC AND PREFORMED PLASTIC PAVEMENT MARKINGS**

618-3 CONSTRUCTION REQUIREMENTS

618-3.01 General

Paragraph c. is revised to read as follows:

c. All markings shall be as shown on the plans, standard drawings or as ordered by the Engineer. Details not shown on the plans shall be in accordance with the current edition of the Manual on Uniform Traffic Control Devices from the Federal Highway Administration (MUTCD-FHWA). All markings shall present a clear cut, uniform and workmanlike appearance. Any markings which fail to have a uniform, satisfactory appearance, either day or night, shall be corrected at the Contractor's expense.

618-3.02 Reflectorized Thermoplastic Markings

d. Application Rates:

Paragraph 3 is revised to read as follows:

3. Glass Beads - Glass beads shall be automatically applied immediately behind the striping mechanism at a rate of one (1) pound per one (1) square meter of thermoplastic surface area.